

STRUCTURAL FORMPLY AS 6669

PRODUCT SPECIFICATIONS

Product:	STRUCTURAL FORMPLY
Veneer Grade:	Class 2 Phenolic Overlay
Standards:	AS 6669 for Plywood – Formwork
Stress Grade:	F11/F14
Manufacturer:	Carter Holt Harvey – Australian & New Zealand Grown & Made
Product Certification:	Engineered Wood Product Association of Australasia (EWPA)
Core Timber Species:	Plantation Pine (Pine, Radiata)
Sheet Size:	2400 x 1200mm
Thicknesses:	12, 17, 19, 25mm
Density:	600kgs/m ³ (approx.)
Glue Bond:	Permanent Type “A” Bond (Phenolic Resin)
Formaldehyde:	Emission “EO”
Applications:	Formwork, horse stables, trailers, etc.

PRODUCT DESCRIPTION

With its durable, smooth and hard-wearing resin impregnated surface and acrylic painted edges, this is an effective solution when used in conjunction with good formwork practices to withstand the rigours of the harsh construction environment.

Finishing

In semi exposed exterior applications, the product must be adequately protected by the use of a suitable water based, exterior paint or stain on both sides of the sheet & edges, irrespective of whether the sides are exposed to the weather or not. It's recommended to contact a reputable paint supplier and follow the manufacturer's instructions. Do not use oil-based products on this plywood as oil-based paints or stains may penetrate the surface veneer of the plywood and react with adhesives that bond the core veneers together. No warranty or guarantee is offered by Plywood & Panel Supplies Pty Ltd (PPS) if oil-based paint or stain has been applied to the plywood. This plywood is not suitable for use in the manufacture of doors and no warranty/ guarantee is offered by PPS if this plywood is utilised in any application associated with the manufacture of doors.

Disclaimer

The information provided herein is believed to be accurate but is not warranted to be, whether it originated with PPS or not. This information cannot be warranted by PPS to be correct or appropriate for the recipient's intended use. Recipients are advised to confirm in advance of need that the information is correct, applicable and suitable to their circumstances. Always refer to manufacturers span tables for correct loadings.