

CD STRUCTURAL H2 TREATED HARDWOOD EXTERIOR PLYWOOD**AS/NZS 2269****PRODUCT SPECIFICATIONS**

Product:	C/D STRUCTURAL H2 HARDWOOD PLYWOOD
Veneer Grade:	C Grade (Face) and D Grade (Back)
Standard:	AS/NZS 2269: 2012 Plywood – Structural
Stress Grade:	F11/ F14/ F17
Veneer Timber Species:	Tropical Hardwood
Core Timber Species:	Tropical Hardwood
Sheet Size:	2400 x 1200mm
Thicknesses:	9mm, 12, 15, 17, 19, 21, 25mm
Density:	580-625kgs/m ³ (approx.)
Glue Bond:	Permanent Type “A” Bond (Phenolic Resin)
Treatment:	Bifenthrin glue line treatment to AS/NZS 1604 to H2 level against borers and termites.
Formaldehyde:	Emission “E0”
Applications:	Flooring, manufacturing, etc.

PRODUCT DESCRIPTION

Fit for use in structural load bearing applications where the stress rating of the plywood meets the relevant building code requirement for that application. This flat, sturdy and stable panel is suitable for tough working conditions requiring impervious durability.

Finishing

In semi exposed exterior applications, the product must be adequately protected by the use of a suitable water based, exterior paint or stain on both sides of the sheet & edges, irrespective of whether the sides are exposed to the weather or not. It's recommended to contact a reputable paint supplier and follow the manufacturer's instructions. Do not use oil-based products on this plywood as oil-based paints or stains may penetrate the surface veneer of the plywood and react with adhesives that bond the core veneers together. No warranty or guarantee is offered by Plywood & Panel Supplies Pty Ltd (PPS) if oil-based paint or stain has been applied to the plywood. This plywood is not suitable for use in the manufacture of doors and no warranty/ guarantee is offered by PPS if this plywood is utilised in any application associated with the manufacture of doors.

Disclaimer

The information provided herein is believed to be accurate but is not warranted to be, whether it originated with PPS or not. This information cannot be warranted by PPS to be correct or appropriate for the recipient's intended use. Recipients are advised to confirm in advance of need that the information is correct, applicable and suitable to their circumstances. Always refer to manufacturers span tables for correct loadings.